

An evaluation of the adhesion of solid oral dosage form coatings to the oesophagus

John D Smart,^{*a} Sian Dunkley,^b John Tsibouklis,^b Simon Young^c

^aDrug Delivery Research Group, School of Pharmacy and Biomolecular Sciences, University of Brighton, Brighton, BN2 4GJ

5 ^bSchool of Pharmacy and Biomedical University Sciences, University of Portsmouth, Portsmouth

^cSchool of Medical Sciences, RMIT University, PO Box 71, Bundoora, Victoria 3083, Australia

*Corresponding Author, +Tel 44 1273 642091, fax: 441273 6420

Email john.smart@brighton.ac.uk

10

Abstract

The impetus for the development of oral dosage forms with extended oesophageal residence time is provided by the strong demand for localised therapies. In parallel, there is considerable demand for the development of technologies that improve the ease of swallowing by minimising oesophageal transit time. Solid oral dosage forms that are coated with a bioadhesive material represent one of the approaches towards either of these goals. This study provides a preliminary assessment of the *in vitro* oesophageal retention characteristics of several widely utilised pharmaceutical coating materials. To this end, a previously described apparatus has been used to measure the force required to pull a coated disc-shaped model tablet across a specified section of excised oesophageal tissue. Of the materials tested, the well-studied mucoadhesive polymer sodium alginate was not only found to be associated with significant oesophageal adhesion properties but also to display the capability to form self-repairing bioadhesive coatings that reformed following damage. Hydroxypropylmethylcellulose also exhibited bioadhesive behaviour but that was less pronounced to that of the alginates. The blending of hydroxypropylmethylcellulose with plasticiser or with low molecular weight polymers and surfactants did not influence bioadhesive behaviour significantly.

25

Low molecular weight water soluble polymers, were found to behave similarly to the uncoated glass control disc. Polysorbates exhibited bioadhesion behaviour that was majorly influenced by the incorporated surfactant. The insoluble polymer ethylcellulose, and the relatively lipophilic surfactant sorbitan monooleate were seen to move over oesophageal tissue more readily than the uncoated glass disc, suggesting that these may be suitable for investigation as coatings for easy-to-swallow solid oral dosage forms.

Keywords: oesophageal adhesion, easy-to-swallow, mucoadhesion, non-adhesive coatings.

35

1. Introduction

The adhesion of solid formulations to the oesophagus during swallowing has been widely implicated in medication-induced injury to this organ. A high local concentration of mucosal irritants (*e.g.* emepronium bromide, apple-cider vinegar, alendronate sodium, tetracycline, potassium chloride) within the oesophagus may lead to oesophageal damage (Hill *et al.*, 2005; Jaspersen, 2000; Ueda *et al.*, 2011). In addition, the extended retention of therapeutic formulations in the oesophagus may impact on the bioavailability and the pharmacokinetics profile of the active. Formulation size, shape and surface characteristics have been identified as factors that influence the adhesion of dosage forms in the oesophagus during swallowing (Channer and Virjee, 1985; Marvola *et al.*, 1982; Perkins *et al.*, 2001).

The adhesion of solid dosage forms to the oesophagus is often desirable, however, since it may provide the means for anchoring formulations designed for the local treatment of gastrooesophageal reflux disease (Batchelor *et al.*, 2002) or for pain and inflammation (Mako *et al.*, 2009), or for delivering diagnostic agents (Collaud *et al.*, 2007).

50

Towards the development of solid oral dosage forms with fine-tuned bioadhesion characteristics, the aim of this study is to provide an *in vitro* assessment of the oesophageal retention behaviour of a range of pharmaceutical coating materials. The bioadhesion evaluation is performed by means of an *in vitro* apparatus (Smart *et al.* 2013), in which adhesive interactions are assessed in terms of the force needed to pull a disc coated with a test material over a flattened section of oesophageal mucosa under physiologically relevant shear stress conditions.

2. Materials and methods

60

2.1 Materials

Hydroxypropylmethylcellulose (HPMC), under the trade names Pharmacoat 615 was supplied by Harke Group, Muelheim an der Ruhr, Germany; The Pluronic™ copolymers F127, F98 and F38 were supplied by BASF PLC, Cheadle, Cheshire. Poly(ethylene glycol) (PEG) 6,000 MW grade (PEG) and Paraffin wax (high melting point, *ca.* 60°C) was purchased from B.D.H Chemicals Ltd, Poole.

65 Polyethylene glycol (PEG) (1,450 mw grade and 200 mw grade), Gelatin (type B, from bovine skin), sodium alginate (medium viscosity grade from *Mactocystis pyrifera*) fluorescein, Type III partially purified mucin, from porcine stomach, triacetin and sorbitan monopalmitate (Span 40) purchased from Sigma-Aldrich Chemical Company, Poole, Dorset. Polyvinyl alcohol (PVA) 15,000 mw grade and ethylcellulose (Ethocel, 10 mPas) were supplied by Fluka Chemicals, Gillingham. LustreClear™ (a microcrystalline cellulose/carrageenan/polyethylene oxide based coating), FMC Biopolymer, Brussels, Belgium.

70 Poly(ethylene oxide), under trade name PolyOx™ (NF grade, NIO) were supplied by Dow chemical company, Belfast.

75

2.2 Preparation of solutions

Dispersions of HPMC (7% w/w), PEG (15 %w/w), sodium alginate (1.5% w/w), gelatin (8% w/w), F127 (10% w/w), Lustraclear™ (9% w/w) and PVA (4% w/w) were all prepared by adding the appropriate
80 mass of polymer to rapidly vortexing (magnetic stirrer) de-ionised water. Mixes were prepared in the proportions of HPMC 7.5% / triacetin 1.5%; HPMC 3% / triacetin 1.5%; HPMC 7.5% PEG 200 1.5%; HPMC 3.75%, triacetin 1.5%, F127 3.75%; PVA 4%, F127 1%. Ethyl cellulose (5% w/w) and sorbitan monopalmitate (7% w/w) were prepared by dissolving in ethanol and isopropanol respectively. All solutions were stored with stirring overnight before use.

85 Simulated saliva was prepared by dissolving 0.9 % sodium chloride solution in deionised water and then adding 0.5% gastric mucin.

Test discs were prepared by casting films from the aqueous polymer solutions using a spin casting
90 technique. The majority of the films were spun at a speed of *ca.* 1000 rpm for 30 seconds, however, the more viscous solutions of HPMC blends and sodium alginate required a higher rotation speed of *ca.* 2000 rpm for 50 seconds. The films were then air-dried (at ambient temperature) and weighed; further applications were applied until a dry constant weight of between 1.50 - 2.00 mg was achieved. Paraffin wax and PEG were melted over a beaker of boiling water. Once molten the glass
95 discs were coated by dipping the surface of each into the molten wax using tweezers and were then allowed to set at room temperature. The films were stored in a dessicator over silica gel and used within 1 week to avoid any discrepancies due physical ageing.

The apparatus consisted of the porcine oesophageal mucoadhesion test system described by Smart
100 *et al.* (2013). Effectively the disc coated with the test material on its lower surface and with a 2 g weight placed on the upper surface is pulled off a PTFE 'non-stick' launch then pulled for 290 s across a distance of 59.5 mm on a flat section of frozen and thawed pig oesophageal mucosa at a 10°

angle with a flow of simulated saliva (1 mL min^{-1}) along the tissue. The force required to move the disc was recorded, and only one test was completed on each tissue. To take into account tissue
105 variances an identical uncoated roughened glass disc was tested on each tissue before adhesion testing with the coated test disc. Each material was tested six times on six different tissues and the corresponding values of the roughened glass controls are also included for each material.

Statistical differences were tested using Analysis of Variance with a Multiple comparison - Tukey's HSD, $p < 0.05$.

110

3. Results

This apparatus measures the resistance to movement of the test disc across the oesophageal mucosa. Two parameters were evaluated: the Maximum Detachment Force (greatest resistance force to
115 movement across the tissue; most often this corresponded with the force associated with resistance to initiate movement across the tissue); and, the work done (area under the force-distance curve over 59.5 mm. To account for differences related to tissue topography, measurements were taken for the test material and for the uncoated plate and then normalised by dividing by the values obtained for the uncoated glass disc on the same tissue sample. The experimental protocol allowed
120 the determination of the adhesion and detachment ratios.

Bioadhesion data for the range of coatings tested is presented on Table 1 and Fig. 2. Of the range of coating materials that have been evaluated sodium alginate and HPMC were found to exhibit the greatest resistance to movement. Interestingly, one of the least adhesive materials was
125 Lustraclear™, which exhibited an initial detachment force that was significantly higher than that seen for the glass plate control. Coatings of PVA or gelatin exhibited behavior that was very similar to that of the uncoated glass plate. The higher molecular weight polyethylene oxide (PolyOx) was characterized by a high resistance to movement, while the structurally related lower molecular

weight PEGs behaved similarly to the glass plate controls (Table 2, Fig 3). The mode of deposition
130 (from the melt or from solution) of the PEG 1450 coating had little effect on the resistance-to-
movement value measured.

Of the three Pluronics tested, only F127 showed a significantly larger adhesion ratio than the
control (Table 3, Fig 4), while the PVA F127 mix exhibited bioadhesion behaviour that was akin to
135 that of the glass plate. F38 was characterized by its very low resistance to the onset of movement,
as were the water insoluble materials ethylcellulose and sorbitan monooleate, both of displayed
lower resistance to movement than the glass plate (Table 4, Fig. 5).

The mixing of HPMC with triacetin (a plasticizer), a pluronic and PEG did not induce a significant
140 effect on the measured bioadhesive properties as compared with those determined for HPMC alone
(Table 5, Fig. 6).

4. Discussion

145 The aim of this study was to use a previously developed test system to evaluate the adhesion of solid
oral dosage form coatings to oesophageal mucosa at physiologically relevant shear stresses. In a
typical force-distance plot, there would be an initial increase (from zero) in the force measured as
tension is applied to the disc. If adhesion is similar to that of controls, the force measured
corresponds to the frictional force of pulling the disc across the mucosa. Bioadhesion is deemed to
150 occur when there is a marked increase in the force measured relative to that for the control. A
reduction in the force required to move the coated plate relative to that needed to move the
roughened glass plate identifies the coating material as non –adhesive/lubricating.

In accord with findings from a previous study, sodium alginate is a material that becomes

155 bioadhesive on hydration (Mortazavi and Smart 1994, Smart 2014). In addition to exhibiting
significant bioadhesion, if dislodged this material was seen to self-repair the adhesive joint by re-
adhering at the next contact point.

In accord with previous reports and owing to the absence of ionisable structural moieties, HPMC,
160 which is employed widely as a tablet coating and also as a bioadhesive in some buccal formulations
(e.g. Suscard Buccal™), is confirmed to be a weaker oesophageal bioadhesive than sodium alginate
(Smart 2014). Gelatin, a protein that is the main component of many soft and hard capsules,
exhibited little evidence of bioadhesive behaviour. Also in accord with previous reports (Mortazavi
and Smart 1995), PVAs, the hydrophilic non-ionic polymers often used as tablet coatings, were found
165 to behave in a similar fashion to the uncoated disc control. LustreClear™, the microcrystalline
cellulose/carrageenan/polyethylene oxide based coating that is marketed as a coating with an
'unparalleled ease of swallowing', behaved similarly in that it showed some bioadhesive properties
on application to the tissue (i.e. some force was required to start to move the plate) but the average
work done to pull the plate across the oesophagus was not significantly different from that obtained
170 for the uncoated glass plate. This bioadhesive behaviour may be explained in terms of the
mucoadhesive component (carrageenan; Mortazavi and Smart 1995) of the coating formulation.

Characterised by the dual capability to mask materials for parenteral administration and to prevent
bacterial biofilm formation (Arciola *et al* 2012), PEGylation may also be reasonably assumed to result
175 in materials that hydrate rapidly and form a lubricating 'slippery mucilage' between the disc and
mucosa. Under the testing protocol employed in this study, however, the behaviour of PEGs was
little different to that of the uncoated disc (Table 2, Fig. 3). It is assumed that this behavior is
consequent to the PEG coating being rapidly removed in an aqueous test environment. Relatively
high molecular weight polyethylene oxide coatings, which have been used as mucoadhesives
180 (Mortazavi and Smart 1995), required an initial strong detachment force to get the disc moving but

adhesion ratios were similar to those of the glass-plate control. Blending the Pluronic™ F127 with a low molecular weight water soluble polymer, such as PVA, reduced the resistance to initial movement to close to that of the glass plate control. Since Pluronic™ surfactants consist of two blocks of hydrophilic polyoxethylene flanking a central hydrophobic polyoxypropylene block, it may be assumed that in aqueous environments the hydrophilic components orientate themselves such that that they become projected outwards from the film to form a hydrated lubricating coating. F38 (average molecular weight, 4700; HLB, 16.1) exhibited bioadhesion behaviour that was insignificantly different to that of the glass plate control. It is possible that it this material becomes rapidly removed from the glass substrate that it coats. F98 (average molecular weight, 13000; HLB, 16) showed some adhesion, notably in the initial detachment force. The less hydrophilic F127 (average molecular weight, 12,600; HLB, 13.8) exhibited significant bioadhesive properties, indicating its unsuitability for use as an 'easy to swallow' tablet coating.

Amongst the materials under evaluation, ethylcellulose, an insoluble tablet coating material, exhibited one of the lowest resistance-to-movement values, presumably by providing a smooth water-repellent coating to glass disc that glides on interfacial water. Similarly, coatings of sorbitan monopalmitate, a sparingly water soluble hydrophobic surfactant with a low HLB value (6.7) also showed a very reduced resistant to movement across the mucosa. The hypothesis of the lubricant effect of interfacial water was further tested with paraffin wax (Drake *et al.*, 2002). As expected, the maximum detachment force and corresponding work done were directionally lower but not significantly different (Multiple comparison - Tukey's HSD, $p < 0.05$) to those obtained with the uncoated glass disc.

The incorporation of a plasticizer (*e.g.* triacetin; commonly used in pharmaceutical coatings) in HPMC (Table 5, Fig. 6) or the mixing of HPMC with a low molecular weight PEG or with a pluronic surfactant did not alter the bioadhesive properties of corresponding coatings.

This work evaluated a range of coating materials for their capability to influence the residence time of a solid dosage form in the oesophagus. A lipophilic surfactant and a water-insoluble polymer have
210 been shown to promote rapid transit, suggesting their suitability as candidate coating materials for easy-to-swallow solid oral formulations. By contrast, known mucoadhesive materials used as coatings slowed the transit of a coated modelled tablet. The work identifies promising oesophageal coating materials, especially for easy-to-swallow solid dosage forms.

215 **References**

- Arciola, C.R., Campoccia, D, Speziale, P, Montanaro, L, Costerton JW. 2012. Biofilm formation in Staphylococcus implant infections. A review of molecular mechanisms and implications for biofilm-resistant materials *Biomaterials* 33, 5967 – 5982.
- Batchelor, H.K., Banning, D., Dettmar, P.W., Hampson, F.C., Jolliffe, I.G., Craig, D.Q.M. 2002. *An in vitro* mucosal model for the prediction of the bioadhesion of alginate solutions to the oesophagus. *Int. J. Pharm.* 238, 123-132.
- Channer K.S. and Virjee J.P. 1985. The effect of formulation of oesophageal transit *J. Pharm. Pharmacol.* 37, 126-129
- Collaud, S., Warloe, T., Jordan, O., Gurny, R., Lange, N. 2007. Clinical evaluation of bioadhesive
225 hydrogels for the topical delivery of hexylaminolevulinate to Barrett’s esophagus. *J. Contr. Rel.* 123, 203-210.
- Drake, W.M., Worsley, D.F., Lentle, B.C., Kandler, D.L. 2002. Monitoring Esophageal transit of wax-polished alendronate in healthy post-menopausal women: a new technique to study of pill transit time. *Current therapeutic research* 63, 103-109.
- 230 Hill, L.L., Woodruff, L.H., Foote, J.C., Barreto-Alcoba, M.A. 2005. Esophageal injury by apple cider vinegar tablets and subsequent evaluation of products. *J. Amer. Dietet. Assoc.* 105, 1141-1143.

Mako, A., Csoka, G., Pasztor, E., Marton, S., Horvai, G., Klebovich, I. 2009. Formulation of thermoresponsive and bioadhesive gel for the treatment of oesophageal pain and inflammation. *Europ J. Pharm Biopharm.* 72, 260-265.

235 Mortazavi, S.A., Smart J.D. 1995. An assessment of some factors influencing the *in vitro* assessment of mucoadhesion. *Int. J. Pharm.* 116, 223-230.

Jaspersen, D. 2000. Drug induced oesophageal disorders. *Drug Safety.* 22(3): 237-249

Marvola, M. Rajaniemi, M., Marttila, E., Vahervuo, K., Sothmann, A. 1982. Effect of dosage form and formulation factors on the adherence of drugs to the oesophagus. *J. Pharm. Sci.* 71(9): 975-977

240 Perkins, A.C., Wilson, C.G., Frier, M., Blackshaw, P.E., Dansereau, R.J., Vincent, R.M., Wenderoth, D., Hathaway, S., Li, Z., Spiller, R.C. 2001. The use of scintigraphy to demonstrate the rapid esophageal transit of the oval film coated placebo risedronate tablet compared to a round uncoated placebo tablet when administered with minimal volumes of water. *Int. J. Pharm.* 222, 295-303.

Smart, J.D., Dunkley, S., Tsibouklis, J., Young, S. 2013. An *in vitro* model for the evaluation of the 245 adhesion of solid oral dosage forms to the oesophagus. *Int. J. Pharm.* 447, 199 – 203.

Smart J.D. Theories of muoadhesion. In *Mucoadhesive Materials and Drug Delivery Systems Ed. V.* Khutoryanskiy John Wiley & Sons Ltd, Chichester 2014 pp159-174.

Ueda, K., Muto, M., Chiba, T. 2011. A case of esophageal ulcer caused by alendronate sodium tablets. *Gastrointestinal endoscopy* 73, 1037.

250 Table 1. Average work done (WD) and maximum detachment forces (MDF) for polymer coatings relative to roughened glass controls, evaluated in the *in vitro* test system.

Material	Film weight / mg (s.d.)	WD / μ J (n =6)	s.d.	MDF / mN (n =6)	s.d.

Sodium alginate	1.96 (0.09)	4154.03	1379.01	263.42	111.39
Glass control		666.35	72.71	13.72	1.11
HPMC	1.73 (0.18)	1209.28	339.70	95.14	43.68
Glass control		665.01	118.83	14.52	2.52
LustreClear	1.74 (0.04)	900.91	44.45	71.52	32.46
Glass control		801.25	127.64	17.31	2.26
PVA	1.92 (0.10)	625.23	57.00	29.11	8.36
Glass control		628.94	73.54	13.44	2.99
Gelatin	1.89 (0.20)	575.25	76.02	19.83	7.61
Glass control		605.51	70.79	12.58	2.03

255

Table 2. Average work done (WD) and maximum detachment forces (MDF) for polyoxyethylene polymer coatings relative to roughened glass controls evaluated in the *in vitro* test system.

Material	Film weight / mg (s.d.)	WD / μ J (n =6)	s.d.	MDF / mN (n = 6)	s.d.
PolyOx	1.98 (0.15)	744.51	80.71	48.98	16.34
Glass control		705.08	47.05	14.77	0.70
PEG 1,450 (solution)	1.90 (0.70)	653.96	91.05	14.37	2.47
Glass control		586.04	71.61	13.00	1.57
PEG 1,450 (Melt)	3.26 (0.15)	611.23	74.51	16.66	1.80
Glass control		559.70	47.38	12.35	2.38
PEG 6,000	1.83 (0.16)	591.50	98.85	12.70	1.84
Glass control		585.49	54.69	12.86	2.05

260

Table 3. Average work done (WD) and maximum detachment forces (MDF) for Pluronic[®] copolymers coatings relative to roughened glass controls evaluated in the *in vitro* test system.

Material	Film weight / mg (s.d.)	WD / μ J (n =6)	s.d.	MDF / mN (n =6)	s.d.
F127	1.82 (0.17)	1121.57	361.05	81.85	37.57
Glass control		526.20	59.86	11.56	1.92
F98	1.88 (0.18)	782.82	83.72	48.67	14.67
Glass control		480.26	59.94	9.98	1.11
F38	1.81 (0.18)	572.16	65.89	13.19	2.34
Glass control		575.21	85.14	12.49	2.33
PVA/F127	1.67 (0.20)	505.29	43.09	20.36	5.21
Glass control		513.65	92.52	10.78	1.84

265

Table 4. Average work done (WD) and maximum detachment force (MDF) values for Hydrophobic coatings and roughened glass controls evaluated in the *in vitro* test system.

Material	Film weight / mg (s.d.)	WD / μ J (n =6)	s.d.	MDF / mN (n =6)	s.d.
Ethylcellulose	1.76 (0.23)	438.52	22.72	8.59	0.59
Glass control		734.46	59.01	16.01	2.03
Paraffin wax	3.5 (0.20)	416.44	54.84	8.61	1.35
Glass control		532.32	57.52	10.60	1.42
Sorbitan monopalmitate	1.98 (0.20)	339.01	29.82	7.01	0.85
Glass control		608.10	89.89	13.07	2.05

270 Table 5. Average work done (WD) and maximum detachment force (MDF) values for polymer blend coatings relative to roughened glass controls evaluated in the *in vitro* test system.

Material	Film weight / mg (s.d.)	WD / μ J (n = 6)	s.d.	MDF / mN (n = 6)	s.d.
HPMC/triacetin (2: 1)	1.93 (0.32)	1095.91	338.49	51.46	22.70
Glass control		570.00	43.67	12.09	1.32
HPMC/triacetin (5:1)	1.86 (0.17)	1244.75	275.32	108.49	35.00
Glass control		603.48	75.18	13.21	3.18
HPMC/PEG 200	1.72 (0.27)	1196.05	169.03	74.05	18.72
Glass control		688.51	37.50	15.71	0.90
HPMC/triacetin/F127	1.93 (0.14)	1297.67	281.96	77.64	29.53
Glass control		625.60	109.85	13.71	2.35

Fig. 1. Schematic diagram of the *in vitro* oesophageal adhesion model

275 Fig. 2. Adhesion and detachment ratios calculated for various coating materials evaluated in the *in vitro* test system (n = 6).

Fig. 3. Adhesion and detachment ratios for the hydrophilic polymers (n=6)

Fig. 4. Adhesion and detachment ratios for the pluronic polymers (n=6)

Fig. 5. Adhesion and detachment ratios for the hydrophobic/insoluble polymers (n=6)

280 Figure 6. Adhesion and detachment ratios calculated for polymer blends relative to HPMC evaluated in the *in vitro* test system (n = 6).





Fig. 2



295 Fig. 3




Fig. 4

300





Fig. 5



305 Fig. 6

